

Epoxy Putties and Adhesives

WEBAC® 4525P CE



WEBAC®

- ▶ WEBAC® 4525P is a special epoxy adhesive which adheres to nearly all substrates even underwater and overhead.

Range of application

- Gluing of mineral building materials underwater
- Concrete protection for floor and wall surfaces according to EN 13813 (CE-Declaration of Performance/4)
- Tubbing, sewer and shaft repair
- Installation of sealing tape on ceilings

Properties


- Overhead application specially for wet substrates
- Universally applicable putty and adhesive material
- Cures underwater and on damp substrates
- Good adhesion to various plastics
- High chemical resistance also to biogenic sulfuric acid
- Adjustable reaction time (accelerator **WEBAC® B45**)
- Total solid*

WEBAC-Chemie GmbH
Fahrenberg 22
22885 Barsbüttel
Germany
Tel. +49 40 67057-0
Fax +49 40 6703227
info@webac.de

www.webac.de

Example

Meaning of the icons ▶ WEBAC Product Catalog,
www.webac.de or www.webac-grouts.com



Repair of tubbing

*according to test method by Deutsche Bauchemie e.V. (German Industry Association for Manufacturers of Construction Chemicals)

▶ Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
© WEBAC-Chemie GmbH. Version 03/17

Epoxy Putties and Adhesives

WEBAC® 4525P CE

Technical data	Values			
Mixing ratio	3 : 1 parts by weight			
Density, 20 °C / 68 °F (ISO 2811)	Comp. A	≈ 1.4 g/cm ³		
	Comp. B	≈ 1.2 g/cm ³		
Apparent density	≈ 1.3 g/cm ³			
Pot life		30 °C / 86 °F ≈ 15 min	20 °C / 68 °F ≈ 25 min	12 °C / 54 °F ≈ 45 min
Application temperature Building structure and material	> 5 °C / 41 °F			
Curing time, 21 °C / 70 °F		5 mm layer thickness ≈ 8 h	8 mm layer thickness ≈ 4.5 h	
Adhesive strength on concrete 7 d, 21 °C / 70 °F (EN 1542)	dry	> 5 N/mm ² , concrete fracture		
	underwater	≈ 3.2 N/mm ² , concrete fracture		
Compressive strength 7 d, 21 °C / 70 °F (ISO 604)	≈ 50 N/mm ²			
Bending tensile strength 7 d, 21 °C / 70 °F (ISO 178)	≈ 55 N/mm ²			
E modulus 7 d, 21 °C / 70 °F (ISO 527)	≈ 4,100 N/mm ²			
Shore hardness D 7 d, 21 °C / 70 °F (EN 868)	≈ 78/70			
CE classification (EN 13813)	SR - B2.0			
Fire behavior	minimum B2 according to DIN 4102-4. 2.3.2			
GISCODE	RE1			
EPD	EPD-DBC-20130033-IBE1-DE			
Exposure scenarios according to REACH	Assessment of industry standard application			

The specified data are values determined under laboratory conditions and are subject to a certain fluctuation. Deviations are possible in practice depending on the respective object situation.

WEBAC-Chemie GmbH
Fahrenberg 22
22885 Barsbüttel
Germany
Tel. +49 40 67057-0
Fax +49 40 6703227
info@webac.de

www.webac.de

► Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
© WEBAC-Chemie GmbH. Version 03/17

Epoxy Putties and Adhesives

WEBAC® 4525P CE



Preparatory work

Structural analysis:

- Inspection of the substrate
 - Moisture condition (dry, damp or wet)
 - Surface strength (> 1.5 N/mm²)
 - Condition of surface (soiled, oily)
- Ensure that the temperature limit is maintained before application
- Remove all dirt, loose and separative substances from the surfaces
- Roughen the surfaces before working on tiles, ceramics or stoneware to improve adhesion



Mixing

- Empty component B in the container of component A (make sure the containers are completely empty) and mix homogenously
- Transfer the mixed material to another clean bucket and stir briefly



Application instruction

- The mixture must be used completely within the specified pot life
- Only use pure WEBAC material without any residues of cleaning agents or other impurity
- The pot life/curing time are influenced by the amount of material/layer thickness and the temperature of the material/building structure – higher temperatures accelerate, lower temperatures slow down the reaction



Application

Patching

- Apply the putty/adhesive with a flat trowel
- For patching apply a layer approx. 10 cm wide and at least 3 mm thick to the entire crack area (also consider subsidiary cracks)
- Depending on the crack course, leave approx. 3–5 cm long sections at the highest points of the crack unpatched to allow the air in the crack to vent



Final work and cleaning

- The patching can be removed mechanically as soon as the injection process is completed and the filling material has cured (e.g. by hot air gun)
- Clean the equipment with **WEBAC® Cleaner A**
- Use **WEBAC® Cleaner B** for dissolving cured material
- Observe the technical data sheets of the cleaners used

WEBAC-Chemie GmbH
Fahrenberg 22
22885 Barsbüttel
Germany
Tel. +49 40 67057-0
Fax +49 40 6703227
info@webac.de

www.webac.de

Epoxy Putties and Adhesives

WEBAC® 4525P CE

Product data					
Application	By flat trowel				
Material consumption	Patching ≈ 500 g/m				
Packing	<table border="1"> <thead> <tr> <th>Comp. A</th> <th>Comp. B</th> </tr> </thead> <tbody> <tr> <td>0.6 kg</td> <td>0.2 kg</td> </tr> </tbody> </table>	Comp. A	Comp. B	0.6 kg	0.2 kg
Comp. A	Comp. B				
0.6 kg	0.2 kg				
Storage	<ul style="list-style-type: none"> Between 8 °C / 46 °F and 25 °C / 77 °F Protect from moisture In original, sealed containers 				
Compatibility/Resistance	<ul style="list-style-type: none"> Compatible with masonry mortar, concrete, steel, foil, cable sheathing and WEBAC injection materials Specially resistant to structurally damaging salts, acids and alkalis 				

WEBAC-Chemie GmbH
 Fahrenberg 22
 22885 Barsbüttel
 Germany
 Tel. +49 40 67057-0
 Fax +49 40 6703227
 info@webac.de

www.webac.de

Test certificates

- Declaration of performance according to Construction Products Regulation
- Test certificate* according to KTW recommendations: D1 (large sealing of surfaces)

Occupational safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or www.webac-grouts.com.

* for drinking water

Waste disposal

In Germany, empty containers can be disposed of via "Interseroh Dienstleistungs GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Information on the disposal and return of WEBAC packaging" in our product catalog or www.webac-grouts.com and the safety data sheets.

► Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
 © WEBAC-Chemie GmbH. Version 03/17